

Contractual Specifications: Chrome Ore 42%

Element/Composition	Weight Percentage
Cr ₂ O ₃	42.00% Base, Rejection: 40.00%
Fe ₂ O ₃	12.00% Max
Cr/Fe Ratio	2.50 Min
Al ₂ O ₃	14.00 % Max
P	0.10 % Max
S	0.10 % Max
SiO ₂	14% Max
MgO	28.00 % Max
Size(10 – 300 mm)	85.00 % Min

Contractual Specifications: Chrome Ore 36%

Element/Composition	Weight Percentage
Cr ₂ O ₃	36.00% Base, Rejection: 34.00%
Fe ₂ O ₃	12.00% Max
Cr/Fe Ratio	2.50 Min
Al ₂ O ₃	9.00 % Max
P	0.10 % Max
S	0.10 % Max
SiO ₂	16.00% Max
MgO	25.00 % Max
Size(10 – 300 mm)	85.00 % Min

Contractual Specifications: Chrome Ore 20%

Element/Composition	Weight Percentage
Cr ₂ O ₃	20.00%
Cr/Fe Ratio	1.50 Min
Al ₂ O ₃	8.00 % Max
P	0.10 % Max
S	0.10 % Max
SiO ₂	16.00% Max
MgO	20.00 % Min
Size(10 – 300 mm)	85.00 % Min