

### Oxidized Bitumen 95/25

Characteristic	Value	Test Method
Specific Gravity @25/25 °C	1.05 Approx.	D-70
Penetration @25 °C	20/30	D-5
Softening Point °C	90/100	D-36
Ductility @25°C	1.5 min	D-113
Loss on Heating (wt)%	0.2 max	D-6
Flash Point °C	260 min	D-92
Solubility in CS <sub>2</sub> (wt)%	99min	D-4