

Bitumen 40/50

Characteristic	Value	Test Method
Specific Gravity @ 25/25°C	1.01-1.06	ASTM D-70
Penetration @ 25°C	40-50	ASTM D-5
Softening Point°C	52-60	ASTM D-36
Ductility @ 25°C	100min	ASTM D-113
Loss On Heating%wt	0.2max	ASTM D-6
Drop In penetration After Heating%	20max	ASTM D-6&D-5
Flash Point°C	250min	ASTM D-92
Solubility In TCE%wt	99.5min	ASTM D-4
Spot Test	Negative	A.A.S.O.T.102*